Research Article

Jiantao Ju*, Zhihong Zhu, Jialiang An, Kangshuai Yang, and Yue Gu

Kinetic study on the reaction between Incoloy 825 alloy and low-fluoride slag for electroslag remelting

<https://doi.org/10.1515/gps-2022-0001>

received June 27, 2021; accepted November 29, 2021

Abstract: A kinetic model for the reactions between the low-fluoride slag $\text{CaF}_2\text{--CaO--Al}_2\text{O}_3\text{--MgO--Li}_2\text{O--TiO}_2$ and Incoloy 825 alloy was proposed based on the two-film theory. The applicability of the model was verified to predict the variation of components in the slag–metal reaction process. The results show that the controlling step of the reaction $4[\text{Al}] + 3(\text{TiO}_2) = 3[\text{Ti}] + 2(\text{Al}_2\text{O}_3)$ is the mass transfer of Al and Ti in the liquid alloy and the controlling step of the reactions $4[\text{Al}] + 3(\text{SiO}_2) = 3[\text{Si}] + 2(\text{Al}_2\text{O}_3)$ and $[\text{Si}] + (\text{TiO}_2) = [\text{Ti}] + (\text{SiO}_2)$ is the mass transfer of SiO_2 in the molten slag. With increasing TiO_2 content in the slag from 3.57% to 11.27%, the Al content in the alloy decreased whereas the Ti content increased gradually. The Si content continued to decrease during the slag–metal reaction. Soluble oxygen in the alloy reacts with Al, Ti, and Si, resulting in a decrease of the oxygen content in the alloy. The variations of TiO_2 content were in good agreement with the calculated results by the kinetic model whereas the measured results of Al_2O_3 and SiO_2 in the slag were lower than the calculated results, which is mainly due to the volatilization of fluoride.

Keywords: low-fluoride slag, kinetics, Incoloy 825 alloy, mass transfer, two film theory

1 Introduction

Incoloy 825 alloy is extensively used in the aerospace and petrochemical industries for its excellent corrosion resistance and mechanical properties [1,2]. Electroslag remelting (ESR) is used to refine Incoloy 825 alloy because it improves the solidification structure of the remelted ingot [3,4] and has the superior ability to remove non-metallic inclusions in liquid steel during ESR [5–7]. However, in the process of producing Incoloy 825 alloy by electroslag remelting, the elements Al and Ti are always lost due to the reaction between the slag components and the alloying elements, which cause the concentrations of the elements to vary from the bottom to the top of the remelted ingot [8,9]. To improve the homogeneity of alloy composition, thermodynamic models [10,11] and kinetic models [12,13] were proposed by researchers to predict the change of alloying element content during ESR.

Many efforts have been carried out to develop the kinetic model to predict the components of ESR. Fraser and Mitchell [14,15] proposed a kinetic model to describe the reaction between FeO in slag and Mn in steel during ESR. Duan et al. [16,17] developed a mass transfer model to expound the desulfurization mechanism. Wei and Mitchell [18,19] elucidated the reaction principle of Al and Si in steel with Al_2O_3 and SiO_2 in the slag to explain the effect of different atmosphere conditions on the loss of elements in steel by proposing a kinetic model of multi-phase reaction of the electroslag process. Hou et al. [20,21] optimized the mass transfer kinetic model of multi-phase reactions during the electroslag remelting process (the reactions are mainly $[\text{Ti}] + (\text{SiO}_2) = [\text{Si}] + (\text{TiO}_2)$, $3[\text{Ti}] + 2(\text{Al}_2\text{O}_3) = 4[\text{Al}] + 3(\text{TiO}_2)$, and $4[\text{Al}] + 3(\text{SiO}_2)$), which could predict the variation of the elements Al, Ti, and Si in the steel and slag components. However, the slag used in the aforementioned models is high-fluorine slag. Li et al. [13] established a kinetic model for the investigation of aluminum and oxidation variations and proposed that the oxygen potential of the slag pool has a better effect

* **Corresponding author: Jiantao Ju**, School of Metallurgical Engineering, Xian University of Architecture and Technology, Xi'an, Shaanxi 710055, China; Research Center of Metallurgical Engineering and Technology of Shaan Xi, Xi'an, China, e-mail: ju_jiantao@163.com

Zhihong Zhu, Jialiang An, Kangshuai Yang, Yue Gu: School of Metallurgical Engineering, Xian University of Architecture and Technology, Xi'an, Shaanxi 710055, China; Research Center of Metallurgical Engineering and Technology of Shaan Xi, Xi'an, China

of improving cleanliness than improving the Al content in the electrode. Fluoride volatilization from the high-fluorine slag not only causes environmental pollution but also changes the composition of the slag and also breaks the equilibrium between the slag and metal. To reduce the volatilization of fluoride in the ESR process, many investigators pay more attention to low-fluorine slag based on its stable composition compared with high-fluorine slag [22–25]. However, the kinetic study of electros slag remelting between low-fluorine slag and Incoloy 825 alloy in the process of electros slag remelting has not been reported.

In the present study, the kinetic model of the reaction process between $\text{CaF}_2\text{--CaO--Al}_2\text{O}_3\text{--MgO--Li}_2\text{O--TiO}_2$ and Incoloy 825 alloy was proposed based on the two-film theory. The variation of the elements Al, Ti, Si, and O in the alloy and the content of each component in the slag were investigated. The mechanism of content change in both slag components and alloying elements and the rate-determining step of the reaction were determined. A slag–metal experiment was proceeded under Ar atmosphere at 1,773 K with different TiO_2 content (3.57%, 7.27%, and 11.28%) of slag to verify the application of the model.

2 Kinetic model

The mass transfer process of each component in the slag–metal reaction is shown in Figure 1. There are three systems of mass transfer in the slag–metal reaction: $\text{Al} + \text{Al}_2\text{O}_3$, $\text{Ti} + \text{TiO}_2$, and $\text{Si} + \text{SiO}_2$. In this experiment, about 0.1% SiO_2 is present in the slag, which may be

Figure 1: Mass transfer diagram of the slag–metal interface (a_O^* is the oxygen activity at the interface).

attributed to the introduction of impurities. Considering the inevitable existence of a little SiO_2 in the industrial slag, therefore, it is of practical significance to consider the $\text{Si} + \text{SiO}_2$ system for industrial production. In order to establish the model, the following assumptions are considered in this model: (1) Only two phases of slag and metal are considered in the slag–metal reaction. (2) Before the reaction, the components in the slag and metal phase are evenly distributed. (3) The interface reacts rapidly and reaches a chemical equilibrium state at the setting temperature. The rate of reactions is controlled by the diffusion of reactants and products through boundary layer at the reacting interface. (4) The slag–metal reaction is not considered from slag addition to melting. (5) The influence of the crucible on the slag–metal reaction is not considered.

The main reactions in the slag–metal reaction can be expressed by Eqs. 1–3:

Considering the thermodynamic equilibrium and the convenience of calculation, Eqs. 1–3 were simplified to Eqs. 4–6:

The expression of equilibrium constants of Eqs. 4–6 is given as Eqs. 7–9 [26–28]:

$$\lg K_{\text{Al}} = \lg \frac{a_{\text{AlO}_{1.5}}^*}{a_{\text{Al}}^* a_{\text{O}}^{*1.5}} = \frac{32,000}{T} - 10.29 \quad (7)$$

$$\lg K_{\text{Ti}} = \lg \frac{a_{\text{TiO}_2}^*}{a_{\text{Ti}}^* a_{\text{O}}^{*2}} = \frac{34,458}{T} - 11.96 \quad (8)$$

$$\lg K_{\text{Si}} = \lg \frac{a_{\text{SiO}_2}^*}{a_{\text{Si}}^* a_{\text{O}}^{*2}} = \frac{30,410}{T} - 11.59 \quad (9)$$

According to the film theory, the diffusion flux of element i at the slag–metal interface is

$$\begin{aligned} J_i &= \frac{k_{i,m} \rho_m}{100 M_i} \{ [\% i] - [\% i]^* \} \\ &= \frac{k_{i,s} \rho_s}{100 M_{iO_x}} \{ (\% iO_x)^* - (\% iO_x) \}, \end{aligned} \quad (10)$$

where J_i is the molar flow, $\text{mol} \cdot \text{m}^{-2} \cdot \text{s}^{-1}$; $k_{i,m}$ and $k_{i,s}$ are the mass transfer coefficients for components in molten alloy and slag; and $k_{\text{Al}} = k_{\text{Ti}} = k_{\text{Si}} = 2 \times 10^{-4} \text{ m} \cdot \text{s}^{-1}$,

$k_{\text{Al}_2\text{O}_3} = k_{\text{TiO}_2} = 1 \times 10^{-5} \text{ m}\cdot\text{s}^{-1}$, and $k_{\text{SiO}_2} = 2 \times 10^{-6} \text{ m}\cdot\text{s}^{-1}$ [29]. M_i and $M_{i\text{O}_x}$ represent molecular weights of alloy and slag components, ρ_m is the density of the alloy, $8,000 \text{ kg}\cdot\text{m}^{-3}$, ρ_s is the density of the slag, $2,650 \text{ kg}\cdot\text{m}^{-3}$, and $[\% i]^*$ and $(\% i\text{O}_x)^*$ are the interfacial concentrations of components in molten alloy and slag.

According to Eq. 11, the interface concentration of element i in the alloy can be expressed as

$$[\% i]^* = \frac{\frac{k_{i,m}\rho_m M_{i\text{O}_x}}{k_{i,s}\rho_s M_i} [\% i] + (\% i\text{O}_x)}{\frac{k_{i,m}\rho_m M_{i\text{O}_x}}{k_{i,s}\rho_s M_i} + B_i a_{\text{O}}^{*x}} \quad (11)$$

where B_i is the apparent equilibrium constant, which is expressed as Eq. 12:

$$B_i = \frac{(\% i\text{O}_x)^*}{[\% i]^* a_{\text{O}}^{*x}} = \frac{M_{i\text{O}_x} f_M K_M \left\{ \frac{(\% \text{CaF}_2)}{M_{\text{CaF}_2}} + \sum \frac{(\% i\text{O}_x)}{M_{i\text{O}_x}} \right\}}{\gamma_{i\text{O}_x}} \quad (12)$$

where K_M is the equilibrium constant, f_M is the activity coefficient of component i in alloy, and $\gamma_{i\text{O}_x}$ is the activity coefficient of component $i\text{O}_x$ in the slag. f_M and $\gamma_{i\text{O}_x}$ are calculated by Eqs. 13 and 14:

$$\lg f_i = \sum (e_i^j [\% j] + r_i^j [\% j]^2) \quad (13)$$

$$\gamma_{i\text{O}_x} = \frac{a_{i\text{O}_x}}{(\% i\text{O}_x)} \quad (14)$$

where e_i^j and r_i^j are the first-order interaction parameter and second-order interaction parameter. The first-order interaction parameters used in the present study are listed in Table 1. The available second-order interaction parameters are summarized as $r_{\text{Al}}^{\text{C}} = -0.004$, $r_{\text{Al}}^{\text{Al}} = (-0.0011 + 0.17/T)$, $r_{\text{Al}}^{\text{Si}} = -0.0006$, $r_{\text{Al}}^{\text{Ni}} = 0.000164$, $r_{\text{Si}}^{\text{Si}} = (-0.0055 + 6.5/T)$, $r_{\text{Si}}^{\text{Cr}} = 0.00043$, $r_{\text{Ti}}^{\text{Ti}} = -0.001$, and $r_{\text{Ti}}^{\text{Ni}} = 0.0005$ [30]. $a_{i\text{O}_x}$ is the activity of components in the slag, calculated by the FactSage7.3 software, and the standard state of activity of components in the slag is the pure substance standard.

The reaction rate of Al, Ti, Si, and O are given as Eqs. 15–18:

$$-\frac{d[\% \text{Al}]}{dt} = \left(\frac{A}{W_m} k_{\text{Al}} \right) \left\{ [\% \text{Al}] - \frac{(\% \text{AlO}_{1.5})}{B_{\text{Al}} a_{\text{O}}^{*1.5}} \right\} \quad (15)$$

$$-\frac{d[\% \text{Ti}]}{dt} = \left(\frac{A}{W_m} k_{\text{Ti}} \right) \left\{ [\% \text{Ti}] - \frac{(\% \text{TiO}_2)}{B_{\text{Ti}} a_{\text{O}}^{*2}} \right\} \quad (16)$$

$$-\frac{d[\% \text{Si}]}{dt} = \left(\frac{A}{W_m} k_{\text{Si}} \right) \left\{ [\% \text{Si}] - \frac{(\% \text{SiO}_2)}{B_{\text{Si}} a_{\text{O}}^{*2}} \right\} \quad (17)$$

$$-\frac{d[\% \text{O}]}{dt} = \left(\frac{A}{W_m} k_{\text{O}} \right) \left\{ [\% \text{O}] - \frac{a_{\text{O}}^*}{f_{\text{O}}} \right\} \quad (18)$$

$$\frac{1}{k_i} = \frac{1}{k_{i,m}\rho_m} + \frac{M_{i\text{O}_x}}{B_i k_{i,s}\rho_s M_i a_{\text{O}}^{*x}} \quad (19)$$

where W_m is the mass of molten steel and k_i is the comprehensive mass transfer coefficient of i . The oxygen activity at the slag–metal interface can be obtained from the above equations and the mass balance equation for oxygen at the interface. Therefore, the following equation can be obtained:

$$\frac{1.5}{M_{\text{Al}}} \cdot \frac{d[\% \text{Al}]}{dt} + \frac{2}{M_{\text{Ti}}} \cdot \frac{d[\% \text{Ti}]}{dt} + \frac{2}{M_{\text{Si}}} \cdot \frac{d[\% \text{Si}]}{dt} - \frac{1}{M_{\text{O}}} \cdot \frac{d[\% \text{O}]}{dt} = 0 \quad (20)$$

The variation of Al_2O_3 , TiO_2 , and SiO_2 in the slag without considering volatilization can be determined on the basis of Eqs. 15–18 and mass conservation.

3 Experimental

Incoloy 825 alloy was smelted in a vacuum induction furnace, and its composition is shown in Table 2. The experimental slag samples were prepared by analytical-grade pure chemical reagents ($\text{CaF}_2 \geq 99\%$, $\text{CaO} \geq 98\%$, $\text{Al}_2\text{O}_3 \geq 99\%$, $\text{MgO} \geq 99\%$, $\text{Li}_2\text{O} \geq 99\%$, $\text{TiO}_2 \geq 99\%$). The CaF_2 and Li_2O reagent powders were heated at 973 K for 4 h, and CaO , Al_2O_3 , MgO , and TiO_2 reagent powders were heated at 1,273 K for 4 h to remove the moisture. The thoroughly mixed powders were melted at 1,773 K for 15 min in a graphite crucible to ensure complete melting and homogenization. When the experiments

Table 1: A first-order interaction parameter e_i^j used in the current study [31–34]

e_i^j	Mn	Cr	Ni	Al	Ti	Cu	Mo	Si	O
Al	0.034	0.045	−0.0376	0.040	—	—	—	—	−34,740/ T + 11.95
Ti	−0.12	0.025	−0.0166	—	0.048	0.014	0.016	—	−1.6
Si	—	−0.021	−0.009	0.058	—	—	—	0.132	−0.23
O	−0.021	−0.032	0.006	7.15−20,600/ T	−0.6	—	—	−0.131	0.734−1,750/ T

Table 2: Chemical composition of the Incoloy 825 alloy (%)

C	Mn	Si	P	S	Cr	Mo	Ni	Cu	Al	Ti	T[O]	Fe
0.101	0.107	0.131	0.009	0.009	20.62	3.18	38.88	1.66	0.12	1.00	0.0026	Bal.

Table 3: Chemical composition of the slag before and after premelting (%)

Slag	Before premelting						After premelting						
	CaF ₂	CaO	Al ₂ O ₃	MgO	Li ₂ O	TiO ₂	CaF ₂	CaO	Al ₂ O ₃	MgO	Li ₂ O	TiO ₂	SiO ₂
N1	23.00	31.70	35.30	2.00	4.00	4.00	20.48	36.13	34.68	1.63	3.21	3.57	0.08
N2	23.00	29.80	33.20	2.00	4.00	8.00	20.62	34.21	32.54	1.49	3.24	7.27	0.11
N3	23.00	27.90	31.10	2.00	4.00	12.00	20.39	32.94	30.25	1.50	3.41	11.28	0.09

were finished, the liquid sample was taken out and quenched quickly on a water-cooled copper plate. Then, the quenched slag samples were pulverized to 200 mesh for chemical analysis. The chemical composition of the slag before and after melting is shown in Table 3.

The equipment for the experiment is shown in Figure 2, where the sample was heated to the target temperature by six MoSi₂ heating elements. The temperature of liquid metal is measured by a B-type reference thermocouple. An Ar flow of 2 L·min⁻¹ is used to prevent the alloy elements from being oxidized by air during the experiment. About 350 g of alloy and 50 g of slag were used in each experiment. The certain reaction time intervals were 5, 10, 15, 20, 25, and 30 min

respectively. Firstly, the alloy was placed in the MgO crucible (Φ 50 mm $\times$ 60 mm). Then, the crucible was placed in a graphite crucible (Φ 70 mm $\times$ 80 mm) to prevent the liquid metal from leaking. The resistance furnace was heated to 1,773 K at a rate of 8 K·min⁻¹ under an Ar atmosphere, holding it at 1,773 K for 10 min to ensure the complete melting of the alloy. Then, 50 g of the slag sample was quickly added into the MgO crucible by a quartz tube having an inner diameter of 10 mm. After reaching the set time, the whole crucible was rapidly removed from the furnace and quenched. The Al, Ti, and Si content in the alloy were determined by inductively coupled plasma-atomic emission spectroscopy. The oxygen content in the alloy was determined by the G8GALILEO oxygen nitrogen hydrogen analyzer, and the chemical composition of the slag was analyzed by X-ray fluorescence.

Figure 2: Schematic diagram of the equipment of the experiment.

4 Results and discussion

4.1 Changes of Al, Ti, and Si content in the alloy

Figure 3 shows the variation of the calculated and measured contents of Al, Ti, Si in the alloy. The content of Al, Ti, and Si in the alloy changing within 15 min indicates that the slag–metal reaction reached the equilibrium at 15 min. As shown in Figure 3a and b, when TiO₂ content in slag increases from 3.57% to 7.27%, the content of Ti in the alloy decreased from 1% to 0.61% and 0.87%, respectively. The Al content in the alloy respectively increased from 0.12% to 0.21% and 0.14%, and the change of Si content in the alloy showed a decreasing trend and was independent of the change in TiO₂ content in the slag.

Figure 3: Experimental and calculated results of the content of Al, Ti, and Si in the alloy: (a) 3.57% TiO_2 , (b) 7.27% TiO_2 , (c) 11.27% TiO_2 .

The equilibrium Al and Ti content and their linear fitting after the slag–metal reaction are shown in Figure 4. It can be seen that the equilibrium Al and Ti content in the alloy show a completely opposite linear relationship. It indicates that elements Ti and Al in the alloy were oxidized by Al_2O_3 and TiO_2 in the slag when the content of TiO_2 was less than 7.27% during the process of slag–metal loss of Ti to increase Al. Moreover, with the increase of TiO_2

content in the slag, the TiO_2 activity increased and enhanced the reactivity with Al in the alloy. The reaction $4[\text{Al}] + 3(\text{TiO}_2) = 3[\text{Ti}] + 2(\text{Al}_2\text{O}_3)$ is going in the positive direction with increasing TiO_2 content. When TiO_2 content in slag was 11.27%, the Ti content in the alloy increased from 1% to 1.18% and Al content decreased from 0.12% to 0.10% during the experiment. It indicates that the element Al in the alloy was oxidized by TiO_2 in the slag, the Gibbs

Figure 4: (a) and (b) Fitting lines of experimental results.

free energy for the reaction $4[\text{Al}] + 3(\text{TiO}_2) = 3[\text{Ti}] + 2(\text{Al}_2\text{O}_3)$ was more negative (the authors have performed the calculation process listed in the literature [35]), leading to the loss of Al and increase of Ti in alloy.

The equilibrium constant expression of Eq. 1 is shown in Eq. 21:

$$\lg \frac{X_{\text{Ti}}^3}{X_{\text{Al}}^4} = \frac{35,300}{T} - 9.94 - \lg \frac{a_{\text{Al}_2\text{O}_3}^2}{a_{\text{TiO}_2}^3} - \lg \frac{f_{\text{Ti}}^3}{f_{\text{Al}}^4} \quad (21)$$

According to Eq. 21, the appropriate value of $\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$ in the slag was 4.24. The activities of Al_2O_3 , TiO_2 , and $\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$ values of three slags were calculated by FactSage as shown in Table 4. It can be seen from Table 4 that the values of $\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$ decreased gradually with the increase of TiO_2 content, and it indicates that the equilibrium Ti content increased and equilibrium Al content decreased. But the values of $\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$ in N1 and N2 slags greater than 4.24. It can be concluded that the Ti content decreased and Al content increased whereas the values of $\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$ in N3 slag was smaller than 4.24. Therefore, the content of Ti and Al in the alloy increased and decreased, respectively. The calculated result was in good agreement with experimental result.

$$\Delta G^\theta = -RT \ln K^\theta \quad (22)$$

$$\Delta G = \Delta G^\theta + RT \ln \frac{a_{\text{TiO}_2}^x}{a_{\text{Al}} \cdot a_{\text{O}}^x} \quad (23)$$

The Gibbs free energy of the reactions according to Eqs. 7–9, 22, and 23 between Si in the alloy, Al_2O_3 , and TiO_2 in the slag were 49.6 and 487.2 kJ·mol⁻¹ respectively, which were both positive. The reaction between oxygen and Si in the liquid alloy was -188 kJ·mol⁻¹, which was negative. It can be concluded that Si in the alloy reacts with oxygen, which is also reason for the changes of the element Si in Figure 3a–c, and it decreased from 0.13% to about 0.04%. The results showed that changes of Al and Ti in the alloy were determined by the reaction $4[\text{Al}] + 3(\text{TiO}_2) = 3[\text{Ti}] + 2(\text{Al}_2\text{O}_3)$.

The calculated results are in good agreement with the experimental results, indicating that the kinetic model proposed by the two-film theory can predict the changes

of Al, Ti, and Si content of the alloy with the progress of the slag–metal reaction.

4.2 Changes of oxygen content in the alloy and mass transfer resistance of the slag–metal reaction

Figure 5 shows the changes of oxygen content in the alloy. Figure 5a–c shows the variation of oxygen in the alloy with N1, N2, and N3 slags during the slag–metal reaction. As shown in Figure 5, the content of oxygen in the alloy continues to decrease, which is caused by the reaction of Al, Ti, and Si in the alloy with oxygen in the alloy under the protection of argon. The changes of Gibbs free energy for Eqs. 4–6 at 1,773 K were -263.4, -253.7, and -188.8 kJ·mol⁻¹, respectively. All of the changes of Gibbs free energy were negative and indicate that Al, Ti, and Si in the alloy reacted with oxygen in the alloy. Moreover, the contents of measured oxygen were higher than the calculated results; this is because that the oxygen content is taken as soluble oxygen in the above theoretical calculation. However, the total oxygen consists of soluble oxygen and oxygen in the form of oxide inclusions. This is consistent with the calculation results of Duan et al. [36].

Table 5 shows the mass transfer resistance of components in the alloy and slag during the progress of the slag–metal reaction. As shown in Table 4, with the increase of TiO_2 content, the mass transfer resistance of TiO_2 in the slag decreased from 0.031 to 0.012 m²·s·kg⁻¹, resulting in an increasing trend of Al oxidation. The mass transfer resistance of Al_2O_3 and SiO_2 changed little. The controlling step of the reaction $4[\text{Al}] + 3(\text{TiO}_2) = 3[\text{Ti}] + 2(\text{Al}_2\text{O}_3)$ was the mass transfer of Al and Ti in the liquid alloy. The controlling step of reactions $[\text{Si}] + (\text{TiO}_2) = [\text{Ti}] + (\text{SiO}_2)$ and $[\text{Al}] + (\text{SiO}_2) = [\text{Si}] + (\text{Al}_2\text{O}_3)$ was the mass transfer of SiO_2 in the molten slag, which caused the low content of SiO_2 in slag.

4.3 Variation of components in the slag

Figure 6 shows the variation of Al_2O_3 , TiO_2 , and SiO_2 in the slag. As shown in Figure 6a, the calculated results of Al_2O_3 are different from the measured results. This is because the initial Al_2O_3 content in the slag is relatively high whereas the Al content in the alloy is low, so the change in Al content has a small effect on the Al_2O_3 content in the slag. Meanwhile, it also can be seen that when

Table 4: Activities of TiO_2 and Al_2O_3 in the slag and values of $\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$ at 1,773 K

Slag	a_{TiO_2}	$a_{\text{Al}_2\text{O}_3}$	$\lg(a_{\text{Al}_2\text{O}_3}^2/a_{\text{TiO}_2}^3)$
N1	1.55×10^{-3}	1.32×10^{-2}	4.67
N2	4.51×10^{-3}	4.78×10^{-2}	4.39
N3	8.17×10^{-3}	8.11×10^{-2}	4.08

Figure 5: Changes of oxygen content in alloys: (a) N1, (b) N2, and (c) N3.

the TiO_2 content increases, the activity of Al_2O_3 also increases. This is due to the combination of TiO_2 and CaO in the slag to form CaTiO_3 . The content of CaO combined with Al_2O_3 decreases, which increases the activity of Al_2O_3 and strengthens the reactivity of CaF_2 . Some researchers have confirmed that AlF_3 volatilization is large in the electroslag system [37,38]. Li et al. [39] also found that the content of Al_2O_3 in the slag decreased after the completion of the industrial electroslag experiment. Therefore, the change in the content of Al_2O_3 in the slag is dominated by the reaction $3\text{CaF}_2 + \text{Al}_2\text{O}_3 = 3\text{CaO} + 2\text{AlF}_3(\text{g})$.

Figure 6b shows that the measured results of TiO_2 content in the slag were in good agreement with the calculated results. The TiO_2 content increased in the N1 and N2 slags and decreased slightly in the N3 slag. The

reaction between Ti in the alloy and Al_2O_3 in the slag caused the increase of TiO_2 content in the N1 and N2 slags, and the decrease of TiO_2 content in the N3 slag was due to the reaction between TiO_2 in the slags and Al in the alloy.

The variation of SiO_2 is shown in Figure 6c. There is a deviation between the measured and calculated results, which is also caused by volatilization. The Si element in the alloy reacts with soluble oxygen to form SiO_2 entering into the slag, and the SiO_2 content in the slag increases at the initial stage of the slag–metal reaction. When the SiO_2 content accumulates to a certain extent, the reaction $\text{CaF}_2 + 2\text{SiO}_2 = \text{CaO} + 2\text{SiF}_4(\text{g})$ [40] occurred. Although the SiO_2 content is small, the vapor pressure of SiF_4 is larger than that of AlF_3 under standard conditions [41], so a

Table 5: Mass transfer resistance of components in the alloy and slag

Slag	Mass transfer resistance of Al, Ti, and Si $\frac{1}{\rho_m \cdot k_{i,m}}$	Mass transfer resistance of Al_2O_3 $\frac{M_{\text{AlO}_{1.5}}}{B_{\text{Al}}M_{\text{AlF}_3}k_s a_0^{*1.5}}$	Mass transfer resistance of TiO_2 $\frac{M_{\text{TiO}_2}}{B_{\text{Ti}}M_{\text{TiF}_3}k_s a_0^{*2}}$	Mass transfer resistance of SiO_2 $\frac{M_{\text{SiO}_2}}{B_{\text{Si}}M_{\text{SiF}_4}k_s a_0^{*2}}$
N1	0.625	9.6×10^{-4}	0.031	11.07
N2	0.625	8.9×10^{-4}	0.019	12.7
N3	0.625	8.9×10^{-4}	0.012	13.1

Figure 6: Changes of Al_2O_3 , TiO_2 , and SiO_2 content in the slag: (a) Al_2O_3 , (b) TiO_2 , and (c) SiO_2 .

small amount of SiF_4 is volatilized and reduces the SiO_2 content in the slag. Compared with the measured result, the Al_2O_3 and SiO_2 content in the slag decreased about 3% and 0.5% respectively, which had no influence on the slag-metal equilibrium. This is supported by the measured and calculated results of Al and Ti content in the alloy as shown in Section 4.1.

The content variation of CaF_2 in the slag is shown in Figure 7. During the process reaction of the slag-metal, the CaF_2 content decreased significantly within 15 min, and then tended to stabilize. The content of Al_2O_3 and

SiO_2 in the slag also changed within 15 min. This proves that the content of CaF_2 , Al_2O_3 , and SiO_2 decreased in the slag because they reacted with each other within 15 min, and the change in the CaF_2 content was not affected by the content of TiO_2 in the slag. The content of all was reduced by about 5% each.

5 Conclusion

1. The experimental results of Al and Ti content in the alloy are in good agreement with the calculated results. The Al content in the alloy decreases with the increase of TiO_2 content in the slag whereas the change of Ti content is the opposite.
2. The content of Si and O in the alloy decreased continuously during the experiment, and the change of Si content was not affected by the change of TiO_2 content in the slag.
3. The controlling step of the reaction $4[\text{Al}] + 3(\text{TiO}_2) = 3[\text{Ti}] + 2(\text{Al}_2\text{O}_3)$ was the mass transfer of Al and Ti in the liquid alloy. The controlling step of reactions $[\text{Si}] + (\text{TiO}_2) = [\text{Ti}] + (\text{SiO}_2)$ and $[\text{Al}] + (\text{SiO}_2) = [\text{Si}] + (\text{Al}_2\text{O}_3)$ was the mass transfer of SiO_2 in the molten slag.

Figure 7: Changes of CaF_2 content in the slag.

4. The measured results of Al_2O_3 and SiO_2 in the slag were lower than the calculated results, which were reduced by about 3% and 0.5%, respectively. The measured results of TiO_2 content were in accordance with the calculated results and change of Ti content in the alloy.

Funding information: National Natural Science Foundation of China (Grant No. 51774225).

Author contributions: Jiantao Ju: writing – original draft, writing – review and editing, methodology, formal analysis; Zhihong Zhu: formal analysis, visualization, project administration; Jialiang An: project administration; Kangshuai Yang: project administration; Yue Gu: project administration.

Conflict of interest: Authors state no conflict of interest.

References

- [1] Sun N, Wen C, Liu ZL, Liu XQ. Effect of Al, Ti contents on the microstructure and corrosion resistance of as-forged Incoloy 825 alloy. *Rare Metal Mat Eng.* 2018;47:860–6.
- [2] Navid S, Morteza S, Behzad N. Arc weldability of Incoloy 825 to AISI 321 stainless steel welds. *J Mater Process Technol.* 2018;262:562–70.
- [3] Li X, Geng X, Jiang ZH, Li HB, Xu FH, Wang LX. Influences of slag system on metallurgical quality for high temperature alloy by electros slag remelting. *Iron Steel.* 2015;50:41–6.
- [4] Zhu QT, Li J, Zhang J, Shi CB, Li JH, Huang J. Precipitation mechanism and reduction of amount of primary carbides during electros slag remelting of 8Cr13MoV stainless steel. *Metall Mater Trans B.* 2019;50:1365–77.
- [5] Shi CB, Park JH. Evolution of oxide inclusions in Si-Mn-killed steel during protective atmosphere electros slag remelting. *Metall Mater Trans B.* 2019;50:1139–47.
- [6] Shi X, Duan SC, Yang WS, Mao MT, Guo HJ, Guo J. Effects of remelting current on structure, composition, microsegregation, and inclusions in Inconel 718 electros slag remelting ingots. *Metall Mater Trans B.* 2019;50:3072–87.
- [7] Hou D, Wang DY, Jiang ZH, Qu TP, Wang HH, Dong JW. Investigation on slag-metal-inclusion multiphase reactions during electros slag remelting of die steel. *Metall Mater Trans B.* 2021;51:478–93.
- [8] Hou D, Jiang ZH, Dong YW, Cao YL, Cao HB, Gong W. Thermodynamic design of electros slag remelting slag for high titanium and low aluminium stainless steel based on IMCT. *Ironmak Steelmak.* 2016;43:1–9.
- [9] Pateisky G, Biele H, Fleischer HJ. The reactions of titanium and silicon with Al_2O_3 – CaO – CaF_2 slags in the ESR process. *J Vac Sci Technol.* 1972;9:1318–21.
- [10] Geng X, Li X, Jiang ZH, Li WM. Thermodynamics model of deoxidation in ESR Process for large slab ingots. *J Northeast Univ.* 2013;43:1132–5.
- [11] Jiang ZH, Hou D, Dong YW, Cao YL, Cao HB, Gong W. Effect of slag on titanium, silicon, and aluminum contents in superalloy during electros slag remelting. *Metall Mater Trans B.* 2016;47:1465–74.
- [12] Shi CB. Deoxidation of electros slag remelting (ESR) – a review. *ISIJ Int* 2020; *ISIJINT* 2019-661. 2020;60:1083–96. doi: 10.2355/isijinternational.ISIJINT-2019-661.
- [13] Li SJ, Cheng GG, Miao ZQ, Chen L, Li CW, Jiang XY. Kinetic analysis of aluminum and oxygen variation of G20CrNi2Mo bearing steel during industrial electros slag remelting process. *ISIJ Int.* 2017;57:2148–56.
- [14] Fraser ME, Mitchell A. Mass transfer in electros slag process: part 1 mass-transfer model. *Ironmak Steelmak.* 1976;5:279–87.
- [15] Fraser ME, Mitchell A. Mass transfer in electros slag process: part 2 mass-transfer coefficients. *Ironmak Steelmak.* 1976;5:288–01.
- [16] Duan SC, Shi X, Wang F, Zhang MC, Li B, Yang WS, et al. Investigation of desulfurization of Inconel 718 superalloys by ESR type slags with different TiO_2 content. *J Mater Res Technol.* 2019;8:2508–16.
- [17] Duan SC, Shi X, Wang F, Zhang MC, Li B, Yang WS, et al. Effect of slag composition on the deoxidation and desulfurization of Inconel 718 superalloy by ESR type slag without deoxidizer addition. *Metall Mater Trans B.* 2020;51:353–64.
- [18] Wei JH, Mitchell A. Changes in composition during A.C. ESR – I theoretical development theoretical mass transfer model. *Acta Metall Sin.* 1984;5:387–05.
- [19] Wei JH, Mitchell A. Changes in composition during A.C. ESR – II laboratory results and analysis. *Acta Metall Sin.* 1984;5:406–13.
- [20] Hou D, Jiang ZH, Dong YW, Gong W, Cao YL, Cao HB. Effect of slag composition on the oxidation kinetics of alloying elements during electros slag remelting of stainless steel: part-1 mass-transfer mode. *ISIJ Int.* 2017;57:1400–9.
- [21] Hou D, Jiang ZH, Dong YW, Gong W, Cao YL, Cao HB. Effect of slag composition on the oxidation kinetics of alloying elements during electros slag remelting of stainless steel: part-2 control of titanium and aluminum content. *ISIJ Int.* 2017;57:1410–9.
- [22] Shi CB, Zheng DL, Shin SH, Li J, Cho JW. Effect of TiO_2 on the viscosity and structure of low-fluoride slag used for electros slag remelting of Ti-containing steels. *Int J Miner Metall Mater.* 2017;24:18–4.
- [23] Zheng DL, Li J, Shi CB, Ju JT. Effect of TiO_2 on the crystallisation behaviour of CaF_2 – CaO – Al_2O_3 – MgO slag for electros slag remelting of Ti-containing tool steel. *Ironmak Steelmak.* 2018;45:135–44.
- [24] Shi CB, Shin SH, Zheng DL, Cho JW, Li J. Development of low-fluoride slag for electros slag remelting: role of Li_2O on the viscosity and structure of the slag. *Metall Mater Trans B.* 2016;47:3343–9.
- [25] Zheng DL, Li J, Shi CB. Development of low-fluoride slag for electros slag remelting: role of Li_2O on the crystallization and evaporation of the slag. *ISIJ Int.* 2020;60:ISIJINT-2019-575–847. doi: 10.2355/isijinternational.ISIJINT-2019-575.
- [26] Hou D, Jiang ZH, Dong YW, Li Y, Gong W, Liu FB. Mass transfer model of desulfurization in the electros slag remelting process. *Metall Mater Trans B.* 2017;48:1885–97.
- [27] Duan SC, Shi X, Mao MT, Yang WS, Han SW, Guo HJ, et al. Investigation of the oxidation behaviour of Ti and Al in Inconel

- 718 superalloy during electroslag remelting. *Sci Rep.* 2018;8:5232.
- [28] Kang JG, Shin JH, Chung Y, Park JH. Effect of slag chemistry on the desulfurization kinetics in secondary refining processes. *Mater Trans B.* 2017;48:2123–5.
- [29] Okuyama G, Yamaguchi K, Takeuchi S, Sorimachi K. Effect of slag composition on the kinetics of formation of Al_2O_3 – MgO inclusions in aluminum killed ferritic stainless steel. *ISIJ Int.* 2000;40:121–8.
- [30] Karasev A, Suito H. Quantitative evaluation of inclusion in deoxidation of Fe-10 mass pct Ni alloy with Si, Ti, Al, Zr, and Ce. *Mater Trans B.* 1999;30:249–57.
- [31] Suzuki K, Ban-Ya S, Hino M. Deoxidation equilibrium of Cr–Ni stainless steel with Si at the temperatures from 1823 to 1923K. *ISIJ Int.* 2002;42:146–9.
- [32] Yoshikawa T, Morita K. Influence of alloying elements on the thermodynamic properties of titanium in molten steel. *Mater Trans B.* 2007;38:671–80.
- [33] Pak JJ, Jeong YS, Tae SJ, Kim DS, Lee YY. Thermodynamics of titanium and nitrogen in an Fe–Ni melt. *Mater Trans B.* 2005;36:489–93.
- [34] Jerzak W, Kalicka Z. Evolution of equilibrium composition of MnO – SiO_2 and Al_2O_3 – MnO – SiO_2 inclusions in liquid Fe and Fe-36% Ni alloy during cooling. *Arch Metall Mater.* 2012;57:449–55.
- [35] Ju JT, An JL, Shi CB, Zheng DL, Ji GH. Reactiveness of low fluorine slag for electroslag remelting to Al and Ti of Incoloy 825 alloy. *Rare Metal Mat Eng.* 2020;49:233–40.
- [36] Duan SC, Shi X, Wang F, Zhang MC, Li B, Yang WS, et al. Investigation of desulfurization of Inconel 718 superalloys by ESR type slags with different TiO_2 content. *J Mater Res Technol.* 2019;8:2508–16.
- [37] Liu Y, Zhao Z, Li GQ, Wu Y, Xu DM, Li BK. Investigation of fluoride vaporization from CaF_2 – CaO – Al_2O_3 slag for vacuum electroslag remelting. *Vacuum.* 2018;158:6–13.
- [38] Shi CB, Cho JW, Zheng DL, Li J. Fluoride evaporation and crystallization behavior of CaF_2 – CaO – Al_2O_3 –(TiO_2) slag for electroslag remelting of Ti-containing steels. *Int J Miner Metall Mater.* 2016;236:627–36.
- [39] Li S, Cheng G, Yang L, Chen L, Yan QZ, Li CW. A thermodynamic model to design the equilibrium slag compositions during electroslag remelting process: description and verification. *ISIJ Int.* 2017;57:713–22.
- [40] Liu Y, Wang Y, Li GQ, Yuan C, Lu R, Li BK. Investigation on the structure, fluoride vaporization and crystallization behavior of CaF_2 – CaO – Al_2O_3 –(SiO_2) slag for electroslag remelting. *J Therm Anal Calorim.* 2020;139:923–31.
- [41] Liang HM, Zhao JX, Zhang ZQ, Li XM, Cui YR. A study on evaporation of fluorides in slag during electroslag remelting process. *Special Steel.* 2012;33:1–3.