Crystal structure of distrontium lanthanum gallium pentaoxide, $\text{Sr}_2\text{LaGaO}_5$

Th. M. Gesing^{*I}, R. Uecker^{II} and J.-Ch. Buhl^I

^I Universität Hannover, Institut für Mineralogie, Welfengarten 1, D-30167 Hannover, Germany

^{II} Institut für Kristallzüchtung, Rudower Chaussee 6, D-12489 Berlin, Germany

Received November 23, 1999, CSD-No. 409463

Abstract

$\text{GaLaO}_5\text{Sr}_2$, tetragonal, $I4/mcm$ (No. 140), $a = 6.9339(4)$ Å, $c = 11.2823(8)$ Å, $V = 542.4$ Å³, $Z = 4$, $R(P) = 0.018$, $wR(P) = 0.027$, $R(I) = 0.031$, $T = 295$ K.

Source of material

$\text{Sr}_2\text{LaGaO}_5$ melts incongruently, therefore it was synthesised by solid state reaction of the single oxides and carbonates, respectively. They were of 4N and 5N quality and the mixture of them was prepared containing SrO , La_2O_3 and Ga_2O_3 in a molar ratio of 4:1:1. The sample was sintered in air in a closed Pt crucible up to 1573 K for 20 h. This reaction led to a homogeneous grey product [1]. Because of the incongruent melting of SrLaGaO_4 - one of the most favoured candidates for substrates for high- T_c superconductors - primary crystallisation of $\text{Sr}_2\text{LaGaO}_5$ takes place when starting the crystal growth from the stoichiometric melt composition SrLaGaO_4 .

Discussion

Preliminary, lattice parameter of this compound were given by Mansmann [2]. The structure of $\text{Sr}_2\text{LaGaO}_5$ is isotypic with $\text{Sr}_2\text{GdGaO}_5$ [3] from which the starting atomic coordinates for the refinement were taken.

Table 1. Data collection and handling.

Powder:	grey
Wavelength:	Mo K_α radiation (0.7093 Å)
μ :	321.3 cm ⁻¹
Diffractometer:	Stoe STADI P
Scan mode:	transmission Debye-Scherrer mode
$2\theta_{\text{max}}$, stepwidth:	59.98°, 0.02°
$N(\text{points})_{\text{measured}}$:	2850
$N(hkl)_{\text{measured}}$:	232
$N(\text{param})_{\text{refined}}$:	30
Program:	RIETAN-97 [4]

Table 2. Atomic coordinates and displacement parameters (in Å²).

Atom	Site	Occ.	x	y	z	U_{iso}
Sr(1)	8h	0.5	0.181(1)	$x+1/2$	0	0.017
La(1)	8h	0.5	0.181	$x+1/2$	0	0.017
Sr(2)	4a	0	0	0	1/4	0.015
Ga(1)	4b	0	0	1/2	1/4	0.018
O(1)	4c	0	0	0	0	0.032
O(2)	16f	0.143(8)	0.143(8)	$x+1/2$	0.642(5)	0.035

References

1. Uecker, R.; Reiche, P.; Ganschow, S.; Uecker, D.-C.; Schultze, D.: Investigation of crystal growth of SrPrGaO_4 and SrLaGaO_4 . *Acta Phys. Pol. A* **92** (1997) 23.
2. Mansmann, M.: Crystal structure of tribariumpentaoxymetallates (IV) and isostructural compounds. *Z. Anorg. Allg. Chem.* **339** (1965) 52.
3. Nguyen Tru Dinh, Fava, J.; Le Flam, G.: Etude structurale et optique de la phase $\text{Sr}_2\text{GdGaO}_5$ dopee a l'euporium trivalent. *Z. Anorg. Allg. Chem.* **433** (1977) 275-283.
4. Izumi, F.: "The Rietveld Method", ed. by R. A. Young, Oxford University Press, Oxford 1993.

* Correspondence author
(e-mail: tm.gesing@mineralogie.uni-hannover.de)