Investigations on the Rare Earth Terpyridyl System

II. Preliminary Observations on the Luminescence of Eu^{3+} and Tb^{3+} Terpyridyl Complexes *

SHYAMA P. SINHA

Cyanamid European Research Institute
Cologny, Geneva, Switzerland

(Z. Naturforschg. **20 a**, 164—165 [1965]; eingeg. am 27. Dezember 1964)

Recently the organic complexes of trivalent rare earths have attracted considerable attention as possible laser materials, where optical pumping can be conveniently carried out resulting in a relatively high fluorescence yield¹⁻¹⁹. All of these studies involved complexes having oxygens as coordinating atoms. In our search for ligands containing atoms other than oxygens and preferably nitrogens as coordination centers we have previously shown²⁰ the intramolecular energy transfer from 2,2'-dipyridyl molecules to the coordinated Sm^{3+} , Eu^{3+} , Tb^{3+} and Dy^{3+} to give rise to line fluorescence characteristics of these coordinated metal ions. Similar fluorescence was observed in the rare-earth-phenanthroline system²¹.

It was of interest to investigate the analogous 2,2',2''-terpyridyl complexes and in this report preliminary observations on the fluorescence characteristics of Eu^{3+} and Tb^{3+} terpyridyl complexes are presented. The absorption spectra of the methanolic solutions of mono-terpyridyl complexes of lighter lanthanides are described elsewhere²² and those of heavier lanthanides will be reported soon.

Fluorescence of the Solid Chelates

By exciting the terpyridyl chelates of Eu^{3+} and Tb^{3+} with long-wave ultraviolet light, the characteristic emissions of the coordinated ions are observed and the data are presented in Table 1. Undoubtedly the fluorescence

of these chelates resulted due to the intramolecular transfer of the absorbed energy by the ligand to the central metal ions. According to the present concept³⁻⁵ of intramolecular energy transfer mechanism, the energy absorbed in the singlet state of the ligand crosses over to the triplet level from where the energy migrates to a low lying 4f-level of the rare earth ion. The transferring level according to FREEMAN and CROSBY⁸ is some higher triplet level than the one from which the phosphorescence originates.

The emission spectra of $\text{Eu}(\text{Terp})\text{Cl}_3 \cdot \text{H}_2\text{O}$ and $\text{Eu}(\text{Terp})_2\text{Cl}_3 \cdot 4\text{H}_2\text{O}$ (Terp = terpyridyl molecule) consist of a large number of lines. The transitions $^5\text{D}_0 \rightarrow ^7\text{F}_1$ and $^5\text{D}_0 \rightarrow ^7\text{F}_2$ of Eu^{3+} in these chelates show a group of three and a group of four lines respectively²³. The observed splitting of $^7\text{F}_1$ may be compared to the similar splitting in europium naphthalate²⁰ and that of $^7\text{F}_2$ to europium-tris-dibenzoylmethide²⁴. A slight shift of these transitions towards higher wave-numbers was noted in the case of europium-bis-terpyridyl chloride chelates. A rough comparison of the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition in europium chelates with neutral nitrogen containing ligands shows a linear relationship of the intensity with the number of coordinated nitrogens. It is also remarkable that the intensity of the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition in the case of dipyrindyl and terpyridyl complexes is higher than in the phthalate and naphthalate complexes. It is possible that the energy transfer through a Eu-O ionic bond is less efficient than a covalent europium-ligand bond. We assume that the intensification of $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transitions in dipyrindyl and terpyridyl complexes is possibly due to a slight intermixing²⁵ of the triplet state of the ligands with the $^5\text{D}_0$ and $^5\text{D}_1$ level of Eu^{3+} .

The strong green fluorescence ($^5\text{D}_4 \rightarrow ^7\text{D}_5$) transition of $\text{Tb}(\text{Terp})(\text{NO}_3)_3$ has also been examined and the transitions originating from the $^5\text{D}_4$ level of Tb^{3+} ($4f^8$) and terminating at the ^7F multiplets viz $^7\text{F}_6$, $^7\text{F}_5$, $^7\text{F}_4$, $^7\text{F}_3$ and $^7\text{F}_2$ have been identified (Table 1).

* Presented at the Conference on Luminescence of Solids, University of Hull, England, September 1964.

¹ S. I. WEISSMAN, J. Chem. Phys. **10**, 214 [1942].

² S. I. WEISSMAN, J. Chem. Phys. **18**, 1258 [1950].

³ G. A. CROSBY, R. E. WHAN, and R. M. ALIRE, J. Chem. Phys. **34**, 743 [1961].

⁴ R. E. WHAN and G. A. CROSBY, J. Mol. Spectr. **8**, 315 [1962].

⁵ G. A. CROSBY, R. E. WHAN, and J. J. FREEMAN, J. Phys. Chem. **66**, 2493 [1962].

⁶ E. NARDI and S. YATSIV, J. Chem. Phys. **37**, 2333 [1962].

⁷ E. J. SCHIMITSCHEK and E. G. K. SCHWARTZ, Nature, Lond. **196**, 832 [1962].

⁸ J. J. FREEMAN and G. A. CROSBY, J. Phys. Chem. **67**, 2717 [1963].

⁹ M. L. BHAUMIK, H. LYONS, and P. C. FLETCHER, J. Chem. Phys. **38**, 568 [1963].

¹⁰ H. WINSTON, O. J. MARSH, C. K. SUZUKI, and C. L. TELK, J. Chem. Phys. **39**, 267 [1963].

¹¹ H. SAMELSON and A. LEMPICKI, J. Chem. Phys. **39**, 110 [1963].

¹² A. LEMPICKI and H. SAMELSON, Phys. Letters **4**, 133 [1963].

¹³ N. E. WOLF and R. J. PRESSLEY, Appl. Phys. Letters **2**, 152 [1963].

¹⁴ E. J. SCHIMITSCHEK, Appl. Phys. Letters **3**, 117 [1963].

¹⁵ M. L. BHAUMIK and C. L. TELK, J. Opt. Soc. Amer. **54**, 1211 [1964].

¹⁶ E. H. HUFFMAN, Nature, Lond. **200**, 158 [1963].

¹⁷ H. SAMELSON, A. LEMPICKI, V. A. BROPHY, and C. BRECHER, J. Chem. Phys. **40**, 2547 [1964].

¹⁸ H. SAMELSON, A. LEMPICKI, and C. BRECHER, J. Chem. Phys. **40**, 2553 [1964].

¹⁹ F. HALVERSON, J. S. BRINEN, and J. R. LETO, J. Chem. Phys. **40**, 2790 [1964]; **41**, 157 [1964].

²⁰ S. P. SINHA, C. K. JØRGENSEN, and R. PAPPALARDO, Z. Naturforschg. **19 a**, 434 [1964].

²¹ L. I. KONONENKO, R. S. LAUER, and N. S. POLUEKTOV, Zh. Analit. Khim. **18**, 1468 [1963]; Chem. Abstr. **60**, 11366 [1964].

²² S. P. SINHA, Part I, Forthcoming paper.

²³ The width of $^7\text{F}_2$ in the mono and bis terpyridyl chelates is approximately $240 \pm 10 \text{ cm}^{-1}$, and that of bis dipyrindyl and naphthalate is 150 and 180 cm^{-1} respectively.

²⁴ A. LEMPICKI and H. SAMELSON, Appl. Phys. Letters **2**, 159 [1963].

²⁵ N. McAVOY, N. FILIPESCU, M. R. KAGAN, and F. A. SERAFIN, J. Phys. Chem. Solids **25**, 461 [1964].

Chelates	Observed fluorescence line (wavenumber in cm^{-1})	Assignments
Eu(Terp)Cl ₃ ·H ₂ O	16835	$^5\text{D}_0 \rightarrow ^7\text{F}_1$
	16181	$^5\text{D}_0 \rightarrow ^7\text{F}_2$
	16129 (Sh)	$^5\text{D}_0 \rightarrow ^7\text{F}_2$
	15380 ^a	$^5\text{D}_0 \rightarrow ^7\text{F}_3$
Eu(Terp) ₂ Cl ₃ ·4 H ₂ O	~ 14390 ^a	$^5\text{D}_0 \rightarrow ^7\text{F}_4$
	16892	$^5\text{D}_0 \rightarrow ^7\text{F}_1$
	16207	$^5\text{D}_0 \rightarrow ^7\text{F}_2$
	15380 ^a	$^5\text{D}_0 \rightarrow ^7\text{F}_3$
Tb(Terp)(NO ₃) ₃	~ 14390 ^a	$^5\text{D}_0 \rightarrow ^7\text{F}_4$
	20284	$^5\text{D}_4 \rightarrow ^7\text{F}_6$
	18349	$^5\text{D}_4 \rightarrow ^7\text{F}_5$
	16949	$^5\text{D}_4 \rightarrow ^7\text{F}_4$
	~ 16000 ^a	$^5\text{D}_4 \rightarrow ^7\text{F}_3$
	~ 15380 ^a	$^5\text{D}_4 \rightarrow ^7\text{F}_2$

^a These lines are observed through a hand spectroscope and are accurate within 100 wavenumbers.

Table 1. Details of fluorescence emission of Eu³⁺ and Tb³⁺ terpyridyl complexes in the solid state at room temperature.

Fluorescence of Methanolic Solutions

The methanolic solutions of europium mono and bis terpyridyl and terbium-terpyridyl complexes fluoresce strongly at room temperature and offer possibilities as potential candidates for liquid laser materials.

A 1 : 2 mixture of methanolic solutions of Eu³⁺ and terpyridyl has a fluorescence lifetime $\tau = 310 \mu\text{s}$ and $\Phi = 0.07$ at room temperature. This τ value may be compared to $\tau = 250 \mu\text{s}$ for bis-dipyridyl complex and $\tau = 80 \mu\text{s}$ for europium-dibenzoylmethide¹¹ solution at room temperature. On lowering the temperature, a decrease of quantum efficiency (Φ) of the 1 : 2 mixture of europium-terpyridyl was noted. This is quite unexpected. Another isolated case where this phenomenon was observed is that of europium acetophenone solu-

tion²⁶. In solution probably the bis-complex is dissociated to the mono-complex and a free terpyridyl molecule. The energy transfer at low temperature being inferior to that at room temperature may be attributed to collision changes with temperature.

A 1 : 1 mixture fluoresces slightly when the components are first mixed and the intensity increases with time. Conductometric titration of the 1 : 1 mixture revealed that the complexation in methanol is slow at room temperature, thus supporting the increase in intensity with time of the 1 : 1 mixture. It seems that in methanolic solutions of the mono-terpyridyl complex, the terpyridyl molecule is bound to the europium ion, and the energy transfer from the ligand to the Eu³⁺ is an intramolecular one. Addition of excess of Eu³⁺ ions to a solution of the solid complex in methanol quenched the fluorescence of the solution. The same effect is obtained with the addition of Gd³⁺ ions.

Experimental

The fluorescence spectra were measured with a Beckman DU spectrophotometer equipped with a fluorescence attachment. Filter no. 22892 (Beckman) was placed between the light source and the sample. Unfortunately the phototube response in the red region and in the yellow of the Beckman instrument is not constant and thus a direct comparison of the $^5\text{D}_0 \rightarrow ^7\text{F}_1$ and $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transitions cannot be made. A Schmidt-Haensch "Longo II" spectroscopy provided with a wavelength scale was also used to observe the emission spectra.

Acknowledgement

The author is indebted to Dr. F. HALVERSON and Dr. J. S. BRINEN of the Central Research Laboratory of American Cyanamid for measuring the lifetimes and taking some phosphorescence spectra.

²⁶ E. MATOVICH and C. K. SUZUKI, J. Chem. Phys. **39**, 1442 [1963].

Untersuchungen an ternären Fluoriden. IV¹

Kristallstruktur von CsNiF₃

DIETRICH BABEL

Laboratorium für Anorganische und Analytische Chemie
der Universität Tübingen

(Z. Naturforsch. **20 a**, 165–166 [1965]; eingeg. am 25. Dezember 1964)

Im Verlaufe systematischer Untersuchungen an Fluorperowskiten¹ wurden die Cäsiumverbindungen CsNiF₃ und CsCuF₃ dargestellt. Einkristalle von CsNiF₃ konn-

ten aus einer langsam abgekühlten Schmelze von 1 CsHF₂ + 1 NiF₂ erhalten werden.

Die Verbindung kristallisiert hexagonal in der Raumgruppe P6₃/mmc – D_{6h}⁴ mit $a = 6,23_6 \text{ \AA}$, $c = 5,22_3 \text{ \AA}$, $c/a = 0,838$ und zwei Formeleinheiten in der Elementarzelle. Mit Cs in 2c, Ni in 2a und F in 6h ergab sich für $x_F = -0,143_1$ ein Zuverlässigkeitswert von $R = 0,065$ (45 Reflexe hkl).

CsNiF₃ ist somit ein weiterer Vertreter des BaNiO₃-Typs², dem auch CsNiCl₃³ angehört. Auf die Verwandtschaft dieser Struktur zum Perowskitgitter ist schon mehrfach hingewiesen worden^{2–5}.

¹ I. Mitteilung: W. RÜDORFF, J. KÄNDLER u. D. BABEL, Z. Anorg. Allg. Chem. **317**, 261 [1962]. — II. Mitteilung: W. RÜDORFF, G. LINCKE u. D. BABEL, *ibid.* **320**, 150 [1963]; III. Mitteilung: D. BABEL, *ibid.*, im Druck.

² J. J. LANDER, Acta Cryst. **4**, 148 [1951].

³ G. N. TISHCHENKO, ref. in Chem. Abstr. **50**, 16251 g [1956].

⁴ B. E. GUSHEE, L. KATZ u. R. WARD, J. Amer. Chem. Soc. **79**, 5601 [1957].

⁵ R. D. BURBANK u. H. T. EVANS, Acta Cryst. **1**, 330 [1948].