Crystal structure of the clathrates $\text{Rb}_8\text{In}_8\text{Ge}_{38}$ and $\text{K}_8\text{In}_8\text{Ge}_{38}$

H. G. von Schnering, H. Menke, R. Kröner, E.-M. Peters, K. Peters

Max-Planck-Institut für Festkörperforschung, Heisenbergstraße 1, D-70569 Stuttgart, Germany

and R. Nesper

ETH Zürich, Laboratorium für Anorganische Chemie, Universitätsstr. 6, CH-8092 Zürich, Switzerland

Received March 3, 1998, transferred to 1st update of database ICSD in 1999, CSD-No. 409253 and CSD-No. 409254

1. $\text{Rb}_8\text{In}_8\text{Ge}_{38}$

Source of material: Stoichiometric mixtures of the elements were sealed in Nb/Ta capsules under Ar, heated up to 1270 K (3 h), annealed at 970 K (2–3 d) and cooled down. $\text{Rb}_8\text{In}_8\text{Ge}_{38}$ forms small crystals. The grey brittle compound is a semiconductor, stable in air and against dilute acids and bases (see ref. 1).

The refinement of the site occupancies results in the composition $\text{Rb}_8\text{In}_n\text{Ge}_{46-n}$ with $n = 7.82 \pm 0.46$. Bond lengths in the E_{46} net (figure): $d1 = 2.525(1)$ Å, $d2 = 2.519(1)$ Å, $d3 = 2.568(1)$ Å, $d4 = 2.641(1)$ Å.

$\text{Ge}_{38}\text{In}_8\text{Rb}_8$, cubic, $Pm\bar{3}n$ (No. 223), $a = 11.033(2)$ Å, $V = 1343.0$ Å³, $Z = 1$, $R(F) = 0.048$, $R_w(F) = 0.031$.

Table 1. Parameters used for the X-ray data collection

Crystal:	grey, metallic luster, size 0.1 x 0.1 x 0.15 mm
Wavelength:	Mo $K\alpha$ radiation (0.71069 Å)
μ :	305.6 cm ⁻¹
Diffractometer:	Nicolet R3m/V
Scan mode:	ω
$T_{\text{measurement}}$:	293 K
$2\theta_{\text{max}}$:	55°
$N(hkl)_{\text{unique}}$:	241
Criterion for I_0 :	$I_0 > 3 \sigma(I_0)$
$N(\text{param})_{\text{refined}}$:	19
Programs:	SHELXS-86, SHELX-76

Table 2. Final atomic coordinates and displacement parameters (in Å²)

Atom	Site	Occ.	x	y	z	U_{11}	U_{22}	U_{33}	U_{12}	U_{13}	U_{23}
Rb1	2a		0	0	0	0.015(1)	U_{11}	U_{11}	0	0	0
Rb2	6d		1/4	1/2	0	0.023(2)	0.035(2)	U_{22}	0	0	0
E1(In)	6c	0.89(1)	1/4	0	1/2	0.015(1)	0.0103(9)	U_{22}	0	0	0
E1(Ge)	6c	0.11	1/4	0	1/2	0.015	0.0103	U_{22}	0	0	0
E2(In)	16i	0.02	0.1839	x	x	0.0116	U_{11}	U_{11}	-0.0010(4)	U_{12}	U_{12}
E2(Ge)	16i	0.98(1)	0.1839(1)	x	x	0.0116(6)	U_{11}	U_{11}	-0.0010(4)	U_{12}	U_{12}
E3(In)	24k	0.09	0	0.3013	0.1164	0.0114	0.0117	0.0110	0	0	-0.0008
E3(Ge)	24k	0.91(1)	0	0.3013(1)	0.1164(1)	0.0114(8)	0.0117(8)	0.0110(8)	0	0	-0.0008(7)

2. K₈In₈Ge₃₈

Source of material: For the synthesis and the chemical properties see above (Rb₈In₈Ge₃₈). K₈In₈Ge₃₈ is also a semiconductor. The grey brittle crystals are small (see ref. 1). Reactions with different In:Ge ratios gave no indications for a homogeneity range (powder pattern) in contrast to ref. 2.

The refinement of the site occupancies results in the composition K₈In_{*n*}Ge_{46-*n*} with *n* = 8.14 ± 0.62. Bond lengths in the E₄₆ net (figure): *d*₁ = 2.528(1) Å, *d*₂ = 2.511(1) Å, *d*₃ = 2.536(1) Å, *d*₄ = 2.642(1) Å.

Ge₃₈In₈K₈, cubic, *Pm* $\bar{3}$ *n* (No. 223), *a* = 10.997(2) Å, *V* = 1329.9 Å³, *Z* = 1, *R*(*F*) = 0.035, *R*_w(*F*) = 0.027.

Table 3. Parameters used for the X-ray data collection

Crystal:	grey, metallic luster, size 0.1 x 0.15 x 0.2 mm
Wavelength:	Mo <i>K</i> _α radiation (0.71069 Å)
μ:	243.2 cm ⁻¹
Diffractometer:	Nicolet R3m/V
Scan mode:	ω
<i>T</i> _{measurement} :	293 K
2θ _{max} :	55°
<i>N</i> (<i>hkl</i>) _{unique} :	237
Criterion for <i>I</i> ₀ :	<i>I</i> ₀ > 3 σ(<i>I</i> ₀)
<i>N</i> (<i>param</i>) _{refined} :	19
Programs:	SHELXS-86, SHELXS-76

Table 4. Final atomic coordinates and displacement parameters (in Å²)

Atom	Site	Occ.	<i>x</i>	<i>y</i>	<i>z</i>	<i>U</i> ₁₁	<i>U</i> ₂₂	<i>U</i> ₃₃	<i>U</i> ₁₂	<i>U</i> ₁₃	<i>U</i> ₂₃
K1	2 <i>a</i>		0	0	0	0.021(2)	<i>U</i> ₁₁	<i>U</i> ₁₁	0	0	0
K2	6 <i>d</i>		1/4	1/2	0	0.031(3)	0.049(3)	<i>U</i> ₂₂	0	0	0
E1(In)	6 <i>c</i>	0.93(1)	1/4	0	1/2	0.0155(8)	0.0129(6)	<i>U</i> ₂₂	0	0	0
E1(Ge)	6 <i>c</i>	0.07	1/4	0	1/2	0.0155	0.0129	<i>U</i> ₂₂	0	0	0
E2(In)	16 <i>i</i>	0.04	0.1836	<i>x</i>	<i>x</i>	0.0134	<i>U</i> ₁₁	<i>U</i> ₁₁	-0.0006	<i>U</i> ₁₂	<i>U</i> ₁₂
E2(Ge)	16 <i>i</i>	0.96(2)	0.1836(1)	<i>x</i>	<i>x</i>	0.0134(4)	<i>U</i> ₁₁	<i>U</i> ₁₁	-0.0006(3)	<i>U</i> ₁₂	<i>U</i> ₁₂
E3(In)	24 <i>k</i>	0.08	0	0.3010	0.1153	0.0137	0.0135	0.0135	0	0	-0.0005
E3(Ge)	24 <i>k</i>	0.92(1)	0	0.3010(1)	0.1153(1)	0.0137(6)	0.0135(6)	0.0135(6)	0	0	-0.0005(4)

References

1. Kröner, R.: Zintl-Phasen der Alkalimetalle und des Bariums mit Clathratstruktur. Dissertation, Universität Stuttgart, 1989.
2. Westerhaus, W.; Schuster, H.-U.: Ternäre Phasen mit modifizierter K₈Ge₄₆-Käfigstruktur. Z. Naturforsch. **32b** (1977) 1365-1367.
3. Sheldrick, G. M.: Phase Annealing in SHELX-90: Direct Methods for Large Structures. Acta Crystallogr. A **46** (1990) 467-473.
4. Sheldrick, G. M.: SHELX-76, Programs for Crystal Structures Determination. Cambridge 1976.